

Technical datasheet

CeNit® 2368

Basic information	Specification
Basic elastomer	PVC (smooth on one side, structured on the other)
Fabric ply	Polyester
Colour	white
Examples of application	Splinter shield for milling machines, tarpaulins

Technical data	Standard term/Specification	Unit	Testing method
Weight	about 600	g/m ²	DIN EN ISO 2286-2
Tensile strength max. (warp)	min. 2.400	N/5m	DIN EN ISO 1421-1
Tensile strength max. (weft)	min. 2.300	N/5m	DIN EN ISO 1421-1
Tear strength (warp)	min. 220	N	DIN53363
Tear strength (weft)	min. 220	N	DIN53363
Low-temperature resistance	- 30	°C	DIN EN 1876-1
Buckling behaviour	min. 100.000	Bucklings	DIN 53359 Procedure A


Legend

n.d. = no data

n.a. = not applicable

Product related special properties may be tested in our in-house laboratory. Where appropriate, individual own and non-DIN-compliant testing standards may be specified.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1119.



elastomer
technology