

# Technical datasheet

## Polyurethane D44

Basic information	Specification
Basic elastomer	Polyurethane
Fabric ply	without ply
Description/features	Premium PU-quality with excellent mechanical properties especially with high wear resistance and elasticity
Format	<b>Sheets:</b> 2 m x 1 m
Colour	tear strength*


Technical data	Standard term/Specification	Unit	Testing method
Density	1.25	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Shore A	available in 70, 80 and 90	°ShA	DIN ISO 7619-1
Tensile strength	40	N/mm <sup>2</sup>	DIN 53504
Elongation at break	600	%	DIN 53504
Abrasion	35	mm <sup>3</sup>	DIN ISO 4649 method A
Tear strength	45	kN/m	DIN ISO 34-1
Tension value at 20% extension	2.5	N/mm <sup>2</sup>	
Tension value at 300% extension	14	N/mm <sup>2</sup>	
Impact resilience	45 at 70 °ShA and 80 °ShA 50 at 90 °ShA	%	DIN 53512
Temperature range	from - 30 to +80	°C	

Resistance	Standard term/Specification
Oil	n.sp.
Fuels	n.sp.
Acids	n.sp.
Alkaline solution	n.sp.
Weather	n.sp.
UV	n.sp.
Note	Volume swell in water: 1 to 2%

Legend
⊕ ⊕ = particularly resistant      ⊖ = not resistant      n.sp. = not specified ⊕ = resistant      n.a. = not applicable

Product-related special properties can be tested in our in-house laboratory. If necessary separate standards and testing standards deviating from DIN may be specified.  
 \*Extreme colour deviations possible depending on manufacturer.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1019.



elastomer  
technology