

# Technical datasheet

## PA 6 FR (Polyamid 6 flame retardant)

Example of application
› vehicle construction; shipbuilding industry; electrical industry; mining

Advantages	Disadvantages
› flame retardant › self-extinguishing › high hardness and mechanical resistance › halogen and phosphorus free › good sliding behaviour and wear performance	› brittle

Basic information	Specification
Format	round material: 12 mm up to 100 mm available in 3 m length sheets: 6 mm up to 90 mm available in 3 m x 0.62 m

Physical properties	Standard term/Specification*	Unit	Testing method
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Moisture ingress	3	%	DIN EN ISO 62

Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	82	MPa	DIN EN ISO 527
Elongation at break	3	%	DIN EN ISO 527
E-Module	3,800	MPa	DIN EN ISO 527
Notch toughness	2	kJ/m <sup>2</sup>	ISO 179
Rochwell hardness	n.sp.	MPa	DIN EN ISO 2039

Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	0.3	W/(m·K)	DIN 52612
Linear thermal expansion coefficient based on a fixed initial length	0.9	K <sup>-1</sup> · 10 <sup>-4</sup>	DIN 53752
	1.8	mm	At initial length of 1.000 mm and a temperature difference of 20 °C.
Max. operating temperature, long-term	85	°C	
Max. operating temperature, short-term	160	°C	
Min. operating temperature, long-term	- 20	°C	

Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	10 <sup>13</sup>	Ω·cm	DIN EN 62631-3-1
Outer surface coefficient	10 <sup>16</sup>	Ω	DIN EN 62631-3-2
Puncture resistance	30	kV/mm	DIN EN 60243

Legend
n.sp. = not specified    n.a. = not applicable

Should you require binding and exact values, please ask for the appropriate factory certificate. This may incur additional costs. Please note that all specifications are standard values only, which are subject to production-related fluctuations.  
\*Higher specification on request.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 1122.



technical  
plastics