

Technical datasheet

PTFE (Polytetrafluorethylene) with 25% GF

Example of application			
› sliding component; seals; linings			
Advantages		Disadvantages	
› excellent anti-friction properties › very high temperature resistance › excellent chemical resistance		› bad mechanical properties › not foodstuff resistant	
Basic information		Specification	
Format		round material: Ø 10 mm up to 250 mm available in 2 m length sheets: 5 mm up to 50 mm available in 1.2 m x 1.2 m	
Physical properties	Standard term/Specification*	Unit	Testing method
Density	2.22	g/cm ³	ISO 1183
Moisture ingress	n.sp.	%	DIN EN ISO 62
Mechanical properties	Standard term/Specification*	Unit	Testing method
Tensile strength	16	MPa	DIN EN ISO 527
Elongation at break	170	%	DIN EN ISO 527
E-Module	n.sp.	MPa	DIN EN ISO 527
Notch toughness	n.sp.	kJ/m ²	ISO 179
Rochwellhardness	n.sp.	MPa	DIN EN ISO 2039
Thermal properties	Standard term/Specification*	Unit	Testing method
Thermal conductivity	n.sp.	W/(m·K)	DIN 52612
Linear thermal expansion coefficient based on a fixed initial length	n.sp.	K ⁻¹ · 10 ⁻⁴	DIN 53752
Max. operating temperature, long-term	260	°C	
Max. operating temperature, short-term	n.sp.	°C	
Min. operating temperature, long-term	-200	°C	
Electrical properties	Standard term/Specification*	Unit	Testing method
Resistance	n.sp.	Ω·cm	DIN IEC 60093
Outer surface coefficient	10 ¹⁵	Ω	DIN IEC 60093
Puncture resistance	13	kV/mm	DIN EN 60243
Legend			
n.sp. = not specified			

Should you require binding and exact values, please ask for the appropriate factory certificate. This may incur additional costs. Please note that all specifications are standard values only, which are subject to production-related fluctuations.

*Higher specification on request.

All information based on current knowledge and experience. Information provided shall not exempt the contractor or user from conducting own tests. A legally binding warranty as to product features or its suitability for specific purposes may not be derived therefrom. Compliance with any proprietary rights as well as existing laws or regulations is the responsibility of the recipient of our products. No liability assumed for printing and any other errors. Technical data subject to change without notice. Reproduction or duplication of this document or its contents - whole or in part - is only permitted with express approval by company noltewerk. The German version of this data shall prevail. As of 0221.



**technical
plastics**